

## G-Grain Product Details

# SOFTSIDE

<b>Market:</b>	<a href="#">Automotive</a>
<b>Content:</b>	Acrylic Topcoat
<b>Backing:</b>	100% Polyester Hi-Loft2
<b>Finishes and Treatments:</b>	Superior Abrasion CFFA 1a, ASTM D-4157 (50,000 cycles, Wyzenbeek #8 cotton duck) Cold Crack -10°F UV Stabilized Pigments (1000 hours, Xenon: AATCC M 16 E / NTC 1479)
<b>Width:</b>	54 in.
<b>Roll Size:</b>	30 yd.
<b>Flame Retardancy*:</b>	California Technical Bulletin 117 Section E FMVSS 302 IMO A.652 (16) Annex I 8.2 & 8.3 NFPA 260 - Class I

\*This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

Our products, when tested with suitable component materials, may comply with California Technical Bulletin 133 and Boston Fire Code (test BFD IX-1).

Certain clothing and accessory dyes (such as those used on denim jeans) may migrate to lighter colors. This phenomenon is increased by humidity and temperature and is irreversible.

Spradling International, Inc. will not assume responsibility for dye transfer caused by external contaminants.