

GENERAL	
Weight	26 ± 10% OZ/YD LIN.
Width	54 inch
Topcoat	PERMABLOK® ADVANCED VINYL PROTECTION PLUS+
Roll Length	30 yd
Composition	PVC
Gauge	39 ± 10% Mills

BACKING	
Description	Hi-Loft™
Weight	5.7 OZ/YD LIN. - ASTM D751
Type	Polyester

SUSTAINABLE PRODUCT PROFILE

SUSTAINABLE MANUFACTURING CERTIFICATIONS

COMPLIANCES

ADDITIONAL TESTS

Tensile Strength Test - ASTM D751 / CFFA-17		
Lbf(Min.)	Warp	121
	Fill	72
Tear Strength - Tongue Method Test - ASTM D751 / CFFA-16b		
Lbf(Min.)	Warp	5.6
	Fill	5.9
Adhesion Test - ASTM D751 / CFFA-3		
Lbf/In(Min.)	Warp	3.3
	Fill	3.3
Crocking Resistant I Test (CFFA - 7)		
-----	Wet	4
	Dry	4
Flex Resistance Test - ASTM D2097 / CFFA-10		
cycles	Warp	30.000 = Pass
	Fill	30.000 = Pass
Cold Crack Test		
CFFA-6a		-10°F

Elongation At Break Test - ASTM D751 / CFFA-17		
%(Ave.)	Warp	67
	Fill	159
Stitching Strength Test - DIN 54301		
Lbf(Min.)	Warp	12
	Fill	8.6
Abrasion Resistant II Test - ASTM D4157 / CFFA-1a		
WYZENBEEK	75.000 Cycles	Pending
Crocking Resistant II Test (AATCC 8)		
-----	Wet	5 - 4/5
	Dry	5 - 4/5
UV stability Test		
Quv	ASTM D-4329 / CFFA-2 c2	Cal≥4 650 Hours = Pass
Blocking Test		
CFFA-4		No.1 - No Blocking ; No Adhesion

FLAME RETARDANCY

US:FMVSS 302	Pass	US:CAL TB 117	Pass
US:NFPA 260 - Cover Fabric	Pass	US:UFAC Fabric Class 1	Pass
EU/US:IMO Res. MSC.307 (88) (FTP 2010 Code) Annex 1 Part 8	Pass		

This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

OTHER ATTRIBUTES

Bacterial Resistant	AATCC 147	Anti Static	ASTM D257
Mildew Resistant	No Growth (NG)	Mildew Resistance Method	ASTM G21
Pink Stain Resistant	Pending		

Note: The data correspond to minimum results of the statistical analysis. The information included in the specification is subject to change.
The indicated data corresponding to the material's physical characteristics are results of test conducted under standard procedures and are subject to variation. We therefore recommend our customers to evaluate the material with regard to the specific requirements and application(s) before specifying. For additional information, please contact your sales representative.
These terms and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.
Spradling group does not assume any responsibility for any damages resulting from improper applications.
Spradling group does not guarantee exact color matches as slight variations in production and stock may occur, as such lot separations is suggested.
Spradling group reserves the right to modify technical sheets without notification.

For a better experience, we recommend opening the file directly in a PDF viewer, and not in the browser.

Conscious of our impact. Designed for the long run.

SPRADLING®
For the long run

V. 12 | Date: June 14, 2025