

NASSIMI

Nassimi LLC T 212.643.8080
370 Seventh Avenue T 800.521.5208
Suite 1600 F 212.643.2626
New York, NY 10001 W www.nassimi.com

Product Specification Sheet

Pattern: Phoenix

Date: 06/ 22/ 2011

STUDIO

General Specifications

Weight (linear yard)	28.0 oz
Width	54 "
Thickness	1.00 mm
Gauge	0.040
Emboss	N/A
Surface Composition	PVC
Substrate Composition	Polyester
Substrate Weight	4.0 oz

General Treatments

UV Resistance	1000 Hours	CFFA-2/ ASTM G26-96 Method C
Cold Crack	-10 F	CFFA-6 Federal Standard No. 191A-Method 5874
Mildew Resistant	Pass	CFFA-120 / ASTM G21-96
Anti-Bacterial	Pass	CFFA-300 / AATCC* Test Method 147-2004
Anti-Microbial	Pass	CFFA-300 / AATCC* Test Method 147-2004
Resilience SR	Pass	
Bleach Resistant	Pass	Diluted 1:10

Physical Strength Properties

Abrasion	250,000 Cycles		CFFA-1A/ Method ASTM D 4157-92
Adhesion	13.0 Warp	12.3 Fill	CFFA 3/ ASTM D751-98
Tear Strength	12.7 Warp	10.4 Fill	CFFA-16/ ASTM D5733-95
Tensile Strength & Elongation	79.4/54.4 Warp	56.0/166.4 Fill	CFFA-17/ ASTM D751-98
Seam Strength	40.0 Warp	29.9 Fill	CFFA-14/ Method ASTM D751-98
Flex Resistance of Finish	25,000 Warp	25,000 Fill	CFFA-10/ ASTM D2097-03(2005)

Flame Retardancy Standards

California Technical Bulletin 117	Pass	NFPA 260	Pass
UFAC Class I	Pass	Boston Fire Code (BFD IX-1)	N/A
BIFMA CS-191-53, Section 3	Pass	IMO A.652(16)8.2	Pass
BIFMA Upholstery, Section 4	Pass	IMO A.652(16)8.3	Pass
MVSS 302	Pass		